

EVER-SILIC[®] LS

ELASTOMERIC SILICONE TOPCOAT

TECHNICAL DATA SHEET

EVER-SILIC[®] LS is a single-component, moisture cured, elastomeric silicone topcoat specifically designed to protect construction wall surfaces from the effects of weather, chemicals, and moisture. Its outstanding features include high solids content, rapid cure and superior physical properties.

FEATURES AND BENEFITS

- Shortened dry time performance.
- Excellent adhesion to polyurethane foam and other roofing membranes.
- Retains flexibility and membrane integrity from -80°F to +250°F.

TYPICAL USES

EVER-SILIC LS provides a durable elastomeric protective coating over sprayed polyurethane roof foam insulation. It can be used by itself as a complete protective coating membrane or as a basecoat with a contrasting-colored topcoat. Superior abrasion resistance is achieved with the addition of ceramic roofing granules embedded into the coating surface.

PRIMER

No primer is necessary over urethane foam or silicone. Consult manufacturer for application to other surfaces.

STANDARD COLORS

White, Light Grey

BUILDING AND FIRE CODES:

EVER-SILIC LS is listed and classified by Underwriters Laboratories Inc. UL 790 Class A as an integral component of numerous roof deck assemblies (File #14330). It is also listed and approved by the California State Fire Marshall.

ADHESION:

EVER-SILIC LS adheres to properly prepared construction roof membrane surfaces, including spray-applied polyurethane or polyisocyanurate foam insulation. It can be re-coated when cured sufficiently to allow light foot traffic, or after 7 to 10 days between coats.

WEATHERING AND ULTRA-VIOLET RESISTANCE:

EVER-SILIC LS has excellent appearance and good flexibility with no checking, cracking or significant discoloration after 8,000 hours of accelerated weathering exposure in an Atlas carbon arc weatherometer according to ASTM D-822. It also has excellent heat resistance to 250°F, good salt, acid and solvent resistance, and moderate alkali resistance.

NOMINAL PROPERTIES

PHYSICAL PROPERTY	TEST METHOD	VALUE	
Dry Time	75°F, 50% RH	>3 hours	
Dry Time w/Accelerator Pkg.	75°F, 50% RH	>2 hours	
Weathering QUV 10,000 hours	ASTM D-822	No Degradation	
Elongation	ASTM D-412	225% ± 15	
Tensile Strength (Die C)	ASTM D-412	500 psi ± 25	
Permanent Set at Break	ASTM D-412	1.0%	
Permanent Change - Heat Aged	ASTM D-412	0%	
Tension Set @ 100%	ASTM D-412	0%	
Water Absorption	ASTM D-570	0.2	
Durometer Hardness: Shore A	ASTM D-2240	45-55	
Permeability (U.S. perms)	ASTM E-96	2.0	
Tear Strength	ASTM D-624	45 psi	
LIQUID PROPERTIES		TEST METHOD	VALUE
Solids by Weight	ASTM D-2697		78± 2%
Solids by Volume	ASTM D-56		66± 2%

CRRC Cool Roof Rating Council SM	Initial		Weathered	
	Solar Reflectance	Thermal Emittance	Rated Product ID	Licensed Manufacturer ID
	.87	.89	0684-0008	0684
				Classification
				Silicone Coating

Cool Roof Rating Council ratings are determined for a fixed set of conditions, and may not be appropriate for determining seasonal energy performance. The actual effect of solar reflectance and thermal emittance on building performance may vary.
Manufacturer of product stipulates that these ratings were determined in accordance with the applicable Cool Roof Rating Council procedures.

APPLICATION:

EVER-SILIC LS is designed to be applied through high pressure airless spray equipment and only by professional applicators. Its theoretical dry film thickness is 10.5 mils when applied at 1 gallon per 100 square feet. The minimum recommended thickness when used as a protective membrane over polyurethane foam is 24 dry mils.

Consult EVERROOF for specific application requirements and end uses.



SHELF LIFE

6 months from the date of manufacture when stored in original unopened containers at temperatures between 32°F and 100°F.

SAFETY, HEALTH & TOXICITY DATA

PROTECTIVE EQUIPMENT: Since the coating is atomized into a very fine particle distribution during spray application, it is essential that maximum effort is made to protect the spray applicator and others near the workplace from undue exposure. This product coating contains polymeric isocyanate (MDI) and as such can be very sensitizing, particularly from vapor inhalation. Some other ingredients in the coating may be sensitizing upon skin contact or eye contact.

CONDITIONS TO AVOID: Avoid open flame or spark sources. Avoid excess heat. Vapors are heavier than air and may travel along the ground or may be moved by ventilation and ignited by pilot lights, other flames, sparks, heaters, smoking, electric motors, or other ignition sources at locations distant from the material handling point. Never use welding or cutting torch on or near drum (even if empty) because product (residue is sufficient hazard) can ignite explosively. In case of fire, use CO₂, steam, dry chemicals, or water fog. Do not use water.

TOXICITY: Contains solvents which require normal precautions in handling materials of this type. Part "A" contains diisocyanate which can be toxic if inhaled as particulate matter.

VAPOR INHALATION: The recommended form of protection against isocyanate or other potentially sensitizing vapors in the workplace is a fresh air supply. Numerous manufacturers, including the 3M Company and MSA, make full-face fresh air masks. For maximum protection, we recommend use of a NIOSH/MESA approved self-contained breathing apparatus with a full-face piece operated in a positive pressure mode. In well-ventilated application conditions, the use of Type C organic vapor cartridge respirators maybe acceptable. Effects of overexposure to vapor are characterized by nasal and respiratory irritation, dizziness, nausea, headache, fatigue, unconsciousness, or even asphyxiation. If ingested and victim is conscious, give large amounts of water or milk to drink. Obtain medical

attention immediately.

SKIN AND EYE CONTACT: To prevent skin contact with the sprayed product, we recommend the use of fabric coveralls and neoprene or other chemically resistant gloves. Skin contact with liquid components can result in a rash or other irritation. Wash any affected skin area with water.

Wipe residual from the skin with a clean cloth, then wipe affected area with a 30% solution of rubbing alcohol. Follow the alcohol wipe with repeated washings with soap and water. If a rash or other irritation develops, see a physician.

Wear a full-face mask or OSHA-approved protective goggles. Eye contact with liquid or spray components can result in corneal burns or abrasions.

Upon exposure, eyes should be flushed with water for an extensive period. Summon emergency trained medical attention immediately.

FLAMMABILITY

Flash point is 115° F. Avoid open flame or spark sources. Avoid excessive heat. Vapors are heavier than air and may travel along the ground or may be moved by ventilation and ignited by pilot lights, other flames, sparks, heaters, smoking, electric motors or other ignition sources at locations distant from the material-handling point. Never use a welding or cutting torch on or near the drum. In case of fire, use CO₂, steam, dry chemicals or water fog.

** This information is intended only as a guide for design purposes. The values shown are the average values obtained from sprayed laboratory samples. The test methods were performed per the ASTM Book of Standards. Higher or lower temperature & humidity conditions will affect dry time.*

The information contained herein is for purposes of identifying the product and does not constitute a warranty that the product will conform

Please read all information in the general guidelines, technical data sheets, application guide, and safety data sheets (SDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local EVERROOF® representative or visit our website for current technical data and instructions. DISCLAIMER: All guidelines, recommendations, statements and technical data contained herein are based on information and tests that EVERROOF® believes to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and/or situation and user assumes all risk and liability resulting from his use of the product(s). EVERROOF® does not suggest or guarantee that any hazards listed herein are the only ones that may exist. EVERROOF® shall not be liable to the user or any third party for any injury, loss, damage, or costs directly or indirectly resulting from use of, or inability to use, the product(s). Recommendations or statements, whether verbal or in writing, other than those contained herein shall not be binding upon EVERROOF®, unless in writing and signed by an authorized corporate officer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and EVERROOF® makes no claim that these tests or any other tests, accurately represent all environments. Not responsible for typographical errors. REV20190820AA