



20 YR SYSTEM QUICK SPEC METAL

High Solids (HS) Silicone Coating System

38 Dry Mil

DESCRIPTION

The EVER-SILIC® COOL ROOF RESTORATION SYSTEM for metal roofs is an elastomeric coating system comprised of either high solids or lower solids spray grade silicone. This high-performance silicone coating system protects the existing roof from the harmful effects of UV, greatly reducing thermal shock and prolonging the life of the roof while helping maintain internal temperatures and reducing cooling costs. It is tested and certified to meet CRRC guidelines for Title 24 compliance.

BASIC USES

The EVER-SILIC COOL ROOF RESTORATION SYSTEM is a tough, durable system designed to extend the life of a wide range of roof top environments from premature weathering and moisture intrusion. It is effective as a protective membrane to coat an entire roof, or to use for spot repair.

FEATURES & BENEFITS

- Prolongs the life of an existing roof surface while helping to lower internal temperatures and reduce cooling costs
- Hydrophobic – highly resistant to water penetration
- High tensile strength and abrasion resistance
- Excellent adhesion to a variety of roof substrates
- Ease of application - extremely fast and simple to install
- Can be used to reinforce and seal seams, penetrations, transitions, terminations, and to make spot repairs
- Economical - extends the life of your existing roof
- Accelerator package is available to shorten cure time
- Can be re-coated up to 7 to 10 days between coats
- UL-790 Class "A" fire resistance rating

WARRANTY

EVERROOF® offers two Limited Warranties:

1. Material Only Warranty - No Charge
2. Labor & Material Warranty - For Approved Applicators Only

Fees and other conditions will apply. Consult your EVERROOF representative. See Warranty System Sheet for Wet and Dry Film Thickness Requirements.


REQUIRED MATERIALS

- EVERROOF Primer M40 Alkyd Metal Primer, or EVERROOF M55 Alkyd Metal Primer
- EVER-SILIC HS High Solids Silicone Base and Top Coat
- EVER-FABRIC 3 oz. Firm 4"
- EVERROOF Webseal with polyester backing
- EVER-SILIC Roof Flash, or EVER-THANE® Roof Flash

Consult your EVERROOF representative for project specific requirements

The EVER-SILIC System provides tenacious adhesion with an existing roof system to form a monolithic membrane. The result is a CRRC rated system that exceeds all Title 24 requirements.

20 YEAR SYSTEM COVERAGE FOR METAL ROOFS - CA



CEMENTS AND COATINGS FOR ROOFING SYSTEMS AS TO EXTERNAL FIRE EXPOSURE (R27681)



SYSTEM DESCRIPTION

The EVER-SILIC system is comprised of options for primer and base and top coats to cover and protect your roof:

1. EVERROOF Primer M40 is a water based, acrylic-metal primer for steel surfaces. Primer M40 is an interior and exterior metal maintenance primer that is free of heavy metal hazards.
2. EVERROOF Primer M55 is a single-component, high solids red oxide alkyd primer for steel surfaces. It is fast drying, rust inhibitive, and easy to apply by brush, spray or roller.
3. EVER-SILIC HS is a single-component, moisture cured, low VOC, elastomeric silicone base and top coat formulated with high volume solids.

STORAGE & HANDLING

Keep containers closed, and store in a dry, cool place away from heat, sparks, open flame, and moisture. Keep material stored above 65°F (18°C) and on wood pallets off concrete floors. Open containers should be blanketed with dry nitrogen before resealing.

ADHESION TEST

To ensure successful application of the EVER-SILIC system always perform several adhesion tests (ASTM D-903) with the coating to ensure the roof substrate will accept the coating. Do not proceed with coating system without prior testing.


PRE-INSPECTION



20 YR QUICK SPEC METAL

EVER-SILIC®

TECHNICAL DATA

Packaging 	1 gal can 5 gal pail 55 gal drum
Coverage Rate Per Gallon	1.5gal/100sq.ft.=24 wet mils
Color	White, Gray, Tan, Custom Colors
Shelf Life	12 Months (unopened)
PHYSICAL PROPERTIES	
Hardness Shore A, ASTM 2240	45-55
Tensile Strength, ASTM D-2370	300 psi (2.07 Mpa)
Tear Strength, ASTM D-624	45 pli (7.88 N/mm)
Elongation, ASTM D-412	200% ± 15
Specific Gravity	1.32
Total Solids by Weight, ASTM D-2697	94% ± 2
Total Solids by Volume, ASTM D-2697	94% ± 2
Viscosity	10,000-15,000 cps
VOC, ASTM D-2369-81	<50 g/liter (0.40 lbs/gal)
Reflectivity 3 years (White)	0.67
Emissivity 3 years (White)	0.90
SRI 3 years (White)	82

Inspect roof for necessary repairs before application of coating system. Inspection should include but not limited to the following:

- HVAC units and flashings
- Ponding water
- Parapet wall conditions
- Wet or damp insulation
- Sign or display anchorage
- Seams, terminations, transitions, and reglets
- Water leakage
- Substrate damage or disrepair
- Proper drainage and obstructions
- Copings and flashings
- Sleepers and pitch pockets

SURFACE PREPARATION

1. Remove all unnecessary and non-functional equipment and debris from the roof.
2. Remove dirt and foreign material detrimental to adhesion or application by thoroughly cleaning all roof surfaces with a high pressure (2,000 - 2,500 psi) (13.79 MPa - 17.24 MPa) wash. Surfaces contaminated with oil, grease, animal fats, etc. must be removed using tri-sodium phosphate and water, or other solutions as required by job conditions and as permitted by local and federal regulations. Remove all cleaning solutions with plenty of fresh water and allow to dry.
3. Metal seam and flashing failures must be repaired by traditional and professional roofing practices. Tighten and/or replace all existing fasteners, install crickets and complete metal sheet work repairs.
4. Prime all areas with EVERROOF Primer M40 or M55 and allow to cure. Detail all roof penetrations, skylights, rake edges, round projections, machine legs, sign posts,

guide wire straps, inside and outside corners, gutters, joints, pipes, voids, protrusions and any areas where water could enter through the roof. Encapsulate all fasteners with EVER-SILIC or EVER-THANE Roof Flash. Clean and seal all drain areas watertight. Use EVER-ROOF Webseal where necessary.

5. On all flat seams apply one pre-coat of EVER-SILIC or EVER-THANE Roof Flash at a rate of 1.5 gallons per 100 sf @ 24 wet mils minimum and embed EVER-FAB-RIC in between layers of wet resin. EVER-SILIC or EVER-THANE Roof Flash shall extend a minimum of 3 inches beyond the edges of the repair.
6. On metal roofs with standing seams apply EVER-SILIC or EVER-THANE Roof Flash to seal them completely.
7. Allow prepared surfaces to become tack free before proceeding with additional priming or coating application. Note: Thickness values of cured film are averages and can vary due to finish of surface. ALWAYS CHECK THE WEATHER PRIOR TO APPLICATION. Depending on the ambient and substrate temperatures, relative humidity, and dew point precautions should be taken when applying materials if precipitation or freezing temperatures are anticipated. Consult product data sheets. Do not apply over wet insulation or related materials.

COATING APPLICATION

1. Apply EVERROOF Primer M40 or Primer M55 SC to the substrate at a theoretical coverage rate of 1/3 gal/100 sf @ 5 wet mils and allow to cure.
2. Apply EVER-SILIC HS base coat at the rate of 1.25 gallons per 100 sf @ 20 wet mils.
3. Apply top coat at the rate of 1.25 gallons per 100 sf @ 20 wet mils, to yield a total of 38 dry mils (minimum requirement for 20-year warranty). Actual required application rate will depend on system specified and length of warranty.

DO NOT EXCEED 2.0 GALLONS PER 100 SF PER APPLICATION for EVER-SILIC HS. This could cause blisters and/or pinholes. Care should be taken to avoid sagging, pinholes, and runs of the coating on vertical, horizontal, and slanted surfaces to prevent sagging. Application rate may need adjusting if coating starts to sag on verticals or higher slopes. Allow base coat and/or top coat to dry 24 hours between coats. Additional coats may be required to achieve required mil thickness. EVER-SILIC Accelerator may be added to speed cure time in cool or dry conditions. Actual required application rate will depend on system specified and length of warranty.

Protection: After completion of application, do not allow traffic on coated surfaces for a period of at least 48 hours at 75°F and 50% R.H., or until completely cured.

EQUIPMENT

Spray Applied - See EVERROOF's Spray Application Guide.

Dipped and Rolled - Brushes of various sizes and a 3/8" nap roller should be used when applying on smooth surfaces such as metal.

THIS QUICK SPEC IS MEANT ONLY AS AN OVERVIEW OF INSTALLATION PROCEDURES. IT IS NOT MEANT TO REPLACE THE DETAILED SPECIFICATION REQUIREMENTS THAT APPEAR IN THE LOW SLOPE RESTORATION SYSTEM SPECIFICATIONS. ALWAYS REVIEW THE DETAILED SPECIFICATION PRIOR TO BEGINNING ANY PROJECT. Published technical data and instructions are subject to change without notice. Contact your local EVERROOF® representative or visit our website for current technical data and instructions. Not responsible for typographical errors. REV20260309.JC